



TECHNICAL DATA SHEET

PSG-3 - Preseintered Grade PTFE Resin

Composition by Weight % and Filler Description

100% Virgin Granular PTFE Resin

MECHANICAL PROPERTIES	TEST METHOD	UNITS	Typical Properties
Specific Gravity	ASTM D 4894	~	2.16 ± 0.02
Tensile Strength*	ASTM D 4894	Mpa	MIN 28
Elongation*	ASTM D 4894	%	MIN 280
Bulk Density	ASTM D 4894	g/l	500 - 600
Hardness	ASTM D 2240	Shore D	58 ± 3
Average Particle Size	INTERNAL	µm	450 - 600
Dielectric Strength	ASTM D4894	KV/mm	60 MIN

General Application:

This grade is suitable for ram extrusion of Rods, Tubes, Profiles and other similar shapes.

Safety

This product is a fluoropolymer so normal precautions should be followed.

Technical Information

DISCLAIMER: the information in this Safety Data Sheet is believed to be correct as of the date issued. No warranties, expressed or implied, including but not limited to, any implied warranty or merchantability or fitness for a particular purpose or course of performance or usage of trade. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of use or application and shall not establish a legally valid contractual relationship.